

3. (Amended) The copper-clad laminate according to claim 1, wherein the prepreg has a glass content of 25 to 70 % by weight.

4. (Amended) The copper-clad laminate according to claim 1, wherein a glass fabric/thermosetting resin base material layer of the copper-clad laminate has a thickness of 30 to 150 μm .

5. (Amended) The copper-clad laminate according to claim 1, wherein the thermosetting resin composition is a resin composition containing, as an essential component, a polyfunctional cyanate ester and a prepolymer of said polyfunctional cyanate ester.